DONGGUAN COWINT NEW MATERIAL TECHNOLOGY CO.,LTD
No.2,West Industrial Road of Jiaoli,Zhongtang Town,Dongguan
Tel: +86-769-88882603 Web:www.cowint.com
E-mail: info@cowint.com

Technical data sheet

CTA-R205 Acrylic Polymer in Primary forms

WATER BASED ACRYLIC

APPLICATION FIELDS

Waterbase Screen printing

APPLICATION PROCESS

1-5%+10-30%binder+water

GENERAL FETAURES

Soft touch

Good 40° C washing fastness Excellent printability

Suitable for Flock Under Base PVC-free

Phthalate-free Formaldehyde-free

Heavy metal-free APEO-free

PREPARATION

Ready to use Ink.

APPLICATION

1-5%+10-30%

CURING:

Curing must take place at 150° C for 02 minutes. Time and temperature must be optimized by the customer, depending on the kind of printing and substrate. In any case, they mustn ’ t be lower than the above-recommended ones.

In verbal or written just the technical advice to show our Companies sincerity, but for our product ,the user companies still have your responsibility for test, to verify whether is suitable for the process and to use; Given the use of the products of our company process conditions are not my company control, and therefore should be fully responsible by the users themselves.