DONGGUAN COWINT NEW MATERIAL TECHNOLOGY CO.,LTD
No.2,West Industrial Road of Jiaoli,Zhongtang Town,Dongguan
Tel: +86-769-88882603 Web:www.cowint.com
E-mail: info@cowint.com

Technical data sheet

CTC-D18G Acrylic Polymer in Primary Forms

1. The printing process

（1）Specially for Metalic digital printing

1)Print the based with CTC-D18B two times —not fixer

2)Print CTC-D18W white paste three times(last time print CMYK directly) —no fixer

3)Printing CTC-D18G with 2 times them (CMYK wet print) after inkjet to be dry

4)After the surface is dry, cover the surface with CTS-G602 (add 2% CTA-F31) 2 times.

5)Curing with 140°-150°/90s-180s

Remarks:

1. Recommended mesh no:43-48T.

In verbal or written just the technical advice to show our Companies sincerity, but for our product ,the user companies still have your responsibility for test, to verify whether is suitable for the process and to use; Given the use of the products of our company process conditions are not my company control, and therefore should be fully responsible by the users themselves.